



EPDM Coatings LLC Products Cross Reference Sheet

<http://www.epdmcoatings.net>

Substrate	Condition	System	Primer	Coverage Per 100 sq ft	Base Coat	Coverage Per 100 sq ft	Finish Coat	Coverage Per 100 sq ft	
Metal Roofing	New (Uncoated)	Water Based (6083)	None Needed. (Mild Acid Etch)		EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal	
		Water Based	None Needed. (Mild Acid Etch)		EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal	
		Solvent Based	None Needed. (Mild Acid Etch)		EnergyGuard Butyl Coating	1.5 gal	EnergyGuard Butyl Coating	1.5 gal	
	Aged Prepainted	Water Based (6083)	PrimeLock Acrylic Primer	0.5 gal	EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal	
		Water Based	PrimeLock Acrylic Primer	0.5 gal	EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal	
		Solvent Based	PrimeLock MultiSurface	0.5 gal	EnergyGuard Butyl Coating	1.5 gal	EnergyGuard Butyl Coating	1.5 gal	
	Mildly Rusted	Water Based (6083)	PrimeLock Metal Primer	0.5 gal	EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal	
		Water Based	PrimeLock Metal Primer	0.5 gal	EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal	
		Solvent Based	PrimeLock MultiSurface	0.5 gal	EnergyGuard Butyl Coating	1.5 gal	EnergyGuard Butyl Coating	1.5 gal	
	<i>** PrimeLock Metal Primer may be used in lieu of PrimeLock MultiSurface on severely rusted surfaces.</i>								
	BUR (Smooth)	No Ponding	Water Based (6083)	PrimeLock Bonding Primer	0.5 gal	EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal
	Mod Bit (Smooth)		Water Based	PrimeLock Bonding Primer	0.5 gal	EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal
Mod Bit (Granulated)	Solvent Based		PrimeLock MultiSurface	0.6 gal	EnergyGuard Butyl Coating	2.0 gal	EnergyGuard Butyl Coating	2.0 gal	
	Mild Ponding	Solvent Based	PrimeLock MultiSurface	0.6 gal	EnergyGuard Butyl Coating	2.0 gal	EnergyGuard Butyl Coating	2.0 gal	
EPDM	No Ponding	Liquid Rubber	None Needed	42	None Needed	1.25 gal	None Needed	1.25 gal	
EPDM	Heavy Ponding	Liquid Rubber	None Needed	0.25 gal	None Needed	1.25 gal	None Needed	1.25 gal	
Hypalon, TPO & PVC	No Ponding	Water Based (6083)	PrimeLock Bonding Primer	0.5 gal	EnergyMax Acrylic Coating	1.25 gal	EnergyMax Acrylic Coating	1.25 gal	
		Water Based	PrimeLock Bonding Primer	0.5 gal	EnergyGuard Acrylic Coating	1.25 gal	EnergyGuard Acrylic Coating	1.25 gal	
	Mild Ponding	Solvent Based	PrimeLock MultiSurface (opt)	0.5 gal	EnergyGuard Butyl Coating	1.25 gal	EnergyGuard Butyl Coating	1.25 gal	
Concrete (Bare)	No Ponding	Water Based (6083)	None Needed if Fully Cured (28 days)		EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal	
		Water Based	None Needed if Fully Cured (28 days)		EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal	
	Mild Ponding	Solvent Based	None Needed if Fully Cured (28 days)		EnergyGuard Aromatic Polyurethane	1.5 gal	EnergyGuard Aromatic Polyurethane	1.25 gal	
Polyurethane Spray Foam	New	Water Based (6083)	None Needed.		EnergyMax Acrylic Coating	1.5 gal	EnergyMax Acrylic Coating	1.5 gal	
		Water Based	None Needed.		EnergyGuard Acrylic Coating	1.5 gal	EnergyGuard Acrylic Coating	1.5 gal	
		Solvent Based	None Needed.		EnergyGuard Silicone Coating	1.25 gal	EnergyGuard Silicone Coating	1.25 gal	

**** EnergyGuard Butyl Coating may be used in lieu of EnergyGuard Silicone Coating for Cold Storage applications. (No warranties.)*

PLEASE REFER TO APPLICATION SPECIFICATIONS FOR ANY WATERPROOFING DETAILS.

N.E Sales Office 494 Bridgeport Ave Suite 101, PMB 342 Shelton CT 06484-4748 • 610-298-1989